

Ultrapure High-Reliability Extruded Solder for Lead-bearing and Lead-free Alloys

Product Description

For soldering applications which require maximum reliability of solder joints, especially for surface mounted components, only solder of the highest purity is acceptable. Kester does not make any vague claims of outstanding solder purity. Complete analysis of Kester Ultrapure Bar Solders prove that every batch conforms to the strictest quality control standards in the solder industry.

Maximum Allowed Impurities

Ultrapure meets the requirements of current industry standards for allowable impurity requirements.

Element	J-STD-006	Kester Ultrapure	Ultra Low Dross
Tin	Balance	Balance	63.5
Lead	0.070	0.070	Balance
Antimony	0.200	0.200	0.050
Copper	0.080	0.080	0.015
Gold	0.050	0.050	0.002
Aluminum	0.005	0.005	0.002
Cadmium	0.002	0.002	0.001
Zinc	0.003	0.003	0.001
Silver	0.100	0.100	0.050
Bismuth	0.100	0.100	0.020
Arsenic	0.030	0.030	0.020
Iron	0.020	0.020	0.010
Indium	0.100	0.100	0.007
Nickel	0.010	0.010	0.002

Ultrapure will conform to these requirements when purchased directly or through stocking distributors. Kester is the only manufacturer of Ultrapure quality solder. Ultrapure conforms to the requirements of J-STD-006 formerly QQ-S-571F. DOD-STD-2000-1A (Soldering Technology, High Quality/High Reliability) states that it is the responsibility of the manufacturer to select those materials and processes that will produce acceptable high quality/high reliability products. Except where otherwise indicated, the component elements in each alloy shall deviate from their nominal mass percentage by not > 0.10% of the alloy mass when their nominal percentage is ≤ 1.0%; by not > 0.20% of the alloy mass when their nominal percentage is > 1.0% to ≤ 5.0% or by not > 0.50% when their nominal percentage is > 5.0%.

Available Alloys

Ultrasure meets the requirements of current industry standards for allowable impurity requirements. Below is a list of typical leaded and lead-free alloys produced by Kester, other alloys can be produced and follow the same requirements.

Leaded Alloys	Melting Point
Sn62Pb36Ag2	179-183°C (354-361°F)
Sn63Pb37	183°C (361°F)
Sn60Pb40	183-190°C (361-374°F)
Sn5Pb92.5Ag2.5	280°C (536°F)

Lead-Free Alloys	Melting Point
Sn96.5Ag3.0Cu0.5	217-220°C (423-428°F)
Sn96.5Ag3.5	221°C (430°F)
Sn97Ag3	221-224°C (430-435°F)
K100LD	~227°C (441°F)
Sn99.3Cu0.7	227°C (441°F)
Sn100	232°C (450°F)
Sn95Sb5	232-240°C (450-464°F)

Storage, Handling and Shelf Life

Kester bar solder has an indefinite shelf life when stored in a dry, non-corrosive environment. The surface may lose its shine and appear a dull shade of gray. This is a surface phenomenon and is not detrimental to product functionality.

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet (SDS) and warning label before using this product.